

Toyobo T-751 Nylon, Painting Grade

Category : Polymer , Thermoplastic , Nylon

Material Notes:

Key Feature: Glass fiber and mineral reinforced, high heat distortion and impact gradesInformation provided by Toyobo Co., Ltd

Order this product through the following link:

http://www.lookpolymers.com/polymer_Toyobo-T-751-Nylon-Painting-Grade.php

Physical Properties	Metric	English	Comments
Density	1.42 g/cc	0.0513 lb/in ³	ASTM D792
Water Absorption	0.70 %	0.70 %	ASTM D570
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	
	@Thickness 3.00 mm	@Thickness 0.118 in	
Linear Mold Shrinkage, Transverse	0.0090 cm/cm	0.0090 in/in	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Ultimate	63.0 MPa	9140 psi	ASTM D638
Elongation at Break	6.0 %	6.0 %	ASTM D638
Modulus of Elasticity	3.30 GPa	479 ksi	ASTM D638
Flexural Yield Strength	108 MPa	15700 psi	ASTM D790
Flexural Modulus	4.00 GPa	580 ksi	ASTM D790
Izod Impact, Notched	1.20 J/cm	2.25 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	40.0 µm/m-°C	22.2 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	210 °C	410 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	167 °C	333 °F	ASTM D648
Flammability, UL94	HB	HB	unregistered

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Strength	21.0 kV/mm	533 kV/in	ASTM D149
	@Thickness 2.00 mm	@Thickness 0.0787 in	
Arc Resistance	120 sec	120 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China