

Tra-Con Tra-Bond 526D01

Category : Polymer , Thermoset

Material Notes:

Information provided by Tra-Con Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tra-Con-Tra-Bond-526D01.php

Physical Properties	Metric	English	Comments
Viscosity	1900 cP @Temperature 25.0 °C	1900 cP @Temperature 77.0 °F	Mixed (lv #4, 12 rpm)

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	87	87	15 min @ 100°C
Adhesive Bond Strength	18.3 MPa	2650 psi	Lap shear, alum to alum, 30 min @ 100°C

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	104 °C	219 °F	Ultimate Tg

Processing Properties	Metric	English	Comments
Cure Time	15.0 min @Temperature 100 °C	0.250 hour @Temperature 212 °F	
Pot Life	120 min	120 min	

Descriptive Properties	Value	Comments
Color	Red Amber	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China