

Tra-Con Tra-Bond 716K02 Thixotropic Adhesive

Category : Polymer , Adhesive , Thermoset , Epoxy

Material Notes:

716K02 is a more thixotropic version of FDA2T. Information provided by Tra-Con Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tra-Con-Tra-Bond-716K02-Thixotropic-Adhesive.php

Physical Properties	Metric	English	Comments
Viscosity	35000 cP	35000 cP	Mixed (cp #52, 10 rpm)

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	82	82	1 hr @ 65°C
Adhesive Bond Strength	16.5 MPa	2400 psi	Lap shear, alum to alum, 1 hr @ 65°C

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	68.0 °C	154 °F	Ultimate Tg; DSC

Processing Properties	Metric	English	Comments
Cure Time	60.0 - 240 min	1.00 - 4.00 hour	
	@Temperature 65.0 °C	@Temperature 149 °F	
	1440 min	24.0 hour	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Descriptive Properties	Value	Comments
Color	Amber	Hardener/Mixed/Cured
	White	Resin
Thixotropic Index	3	1 rpm/10 rpm

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

