

Trelleborg Emerson & Cuming Eccobond® 15 Variable Hardness Catalyst

Category : Polymer , Adhesive , Thermoset

Material Notes:

Emerson & Cuming 15 Eccobond® Variable Hardness Catalyst Easy-to-use, simple mix ratios. Hardness of cured castings can be controlled by the amount of hardener used. Long working life. Yields cured castings or adhesives having outstanding adhesion to a wide variety of substrates. Very low peak exotherm. Cure Type: Room Temp or Heat

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Eccobond-15-Variable-Hardness-Catalyst.php

Physical Properties	Metric	English	Comments
Density	0.970 g/cc	0.0350 lb/in³	
Viscosity	25000 cP @Temperature 25.0 °C	25000 cP @Temperature 77.0 °F	Mixed

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	90.0 °C	194 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	120 - 240 min @Temperature 65.0 °C	2.00 - 4.00 hour @Temperature 149 °F	
	960 - 1440 min @Temperature 25.0 °C	16.0 - 24.0 hour @Temperature 77.0 °F	
Pot Life	120 min @Temperature 25.0 °C	120 min @Temperature 77.0 °F	100 grams

Descriptive Properties	Value	Comments
Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China