

Trelleborg Emerson & Cuming Eccobond® 26 Two-Component General Purpose Epoxy Adhesive

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy Adhesive

Material Notes:

Emerson & Cuming 26 Eccobond® Two-Component General Purpose Epoxy Adhesive Filled, room temperature curing, general purpose, epoxy adhesive. Recommended for varied uses including repair and manufacture of tools, furniture, boats, and electronic sub-assemblies.

Mix Ratio of 100:100. Bonding Type: Epoxy

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Eccobond-26-Two-Component-General-Purpose-Epoxy-Adhesive.php

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in³	

Mechanical Properties	Metric	English	Comments
Adhesive Bond Strength	14.5 MPa	2100 psi	

Processing Properties	Metric	English	Comments
Cure Time	19.8 min	0.330 hour	
	@Temperature 65.0 °C	@Temperature 149 °F	
	240 min	4.00 hour	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Descriptive Properties	Value	Comments
Color	Off-white	
Viscosity	Thixotropic Paste	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China