

Trelleborg Emerson & Cuming Eccobond® 286 Two-Component General Purpose Epoxy Adhesive

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy Adhesive , Epoxy, Thermally Conductive

Material Notes:

Emerson & Cuming 286 Eccobond® Two-Component General Purpose Epoxy Adhesive Filled, general purpose, thermally conductive, epoxy adhesive. Room temperature cure. Convenient mix ratio. Recommended for a wide variety of maintenance and production applications.

Ideal for use in piping applications involving metal and plastic pipe. Mix ratio of 100:100 (volume). Bonding Type: Epoxy

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Eccobond-286-Two-Component-General-Purpose-Epoxy-Adhesive.php

Physical Properties	Metric	English	Comments
Density	1.71 g/cc	0.0618 lb/in³	

Mechanical Properties	Metric	English	Comments
Adhesive Bond Strength	15.2 MPa	2200 psi	

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	
	@Temperature 65.0 °C	@Temperature 149 °F	
	240 min	4.00 hour	
	@Temperature 45.0 °C	@Temperature 113 °F	
	1440 min	24.0 hour	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Descriptive Properties	Value	Comments
Color	White	
Viscosity	Thixotropic Paste	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China