

Trelleborg Emerson & Cuming Eccobond® G 909 One-Component Fast Cure Epoxy Adhesive

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy Adhesive

Material Notes:

Emerson & Cuming G 909 Eccobond® One-Component Fast Cure Epoxy Adhesive High strength, thixotropic, flexible, epoxy adhesive. High peel strength (30 pli). Recommended for bonding copper, aluminum and fiberglass reinforced plastics. Good bonds to oily steel. Cure Type: Heat Bonding Type: Epoxy

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Eccobond-G-909-One-Component-Fast-Cure-Epoxy-Adhesive.php

Physical Properties	Metric	English	Comments
Density	1.15 g/cc	0.0415 lb/in³	

Mechanical Properties	Metric	English	Comments
Adhesive Bond Strength	40.0 MPa	5800 psi	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 °C	302 °F	
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	20.0 min	0.333 hour	
	@Temperature 150 °C	@Temperature 302 °F	
	30.0 min	0.500 hour	
	@Temperature 120 °C	@Temperature 248 °F	
	90.0 min	1.50 hour	
	@Temperature 100 °C	@Temperature 212 °F	

Descriptive Properties	Value	Comments
Color	Grey	
Viscosity	Thixotropic Paste	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China