

Trelleborg Emerson & Cuming Stycast® 1365-25 Two-Component Epoxy Flexible Encapsulant

Category : Polymer , Adhesive , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Emerson & Cuming 1365-25 Stycast® Two-Component Epoxy Flexible Encapsulant Features Good Chemical Resistance Unfilled Low

Viscosity Mix Ratio (by weight) = 100:100 Cure Type: Room Temp or Heat Bonding Type: Epoxy

Order this product through the following link:

http://www.lookpolymers.com/polymer_Trelleborg-Emerson-Cuming-Stycast-1365-25-Two-Component-Epoxy-Flexible-Encapsulant.php

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in³	
Viscosity	150 cP @Temperature 25.0 °C	150 cP @Temperature 77.0 °F	Mixed

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	25	25	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	90.0 °C	194 °F	
Minimum Service Temperature, Air	-55.0 °C	-67.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Constant	4.0 @Frequency 1e+6 Hz	4.0 @Frequency 1e+6 Hz	

Processing Properties	Metric	English	Comments
Cure Time	>= 120 min	>= 2.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China