

UBE UBEPOL VCR617 Synthetic Rubber Vulcanizate (Cured 50 Minutes at 145°C)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Description: UBEPOL-VCR is a new type of synthetic rubber system developed by UBE's original technology. UBEPOL-VCR consists of micro-dispersed syndiotactic 1,2-polybutadiene (SPB) with high melting point and crystallinity, and high cis-1,4-polybutadiene rubber matrix. UBEPOL-VCR is improved on the processability and a lot of physical properties of the conventional polybutadiene rubber (BR). Information provided by UBE.

Order this product through the following link:

http://www.lookpolymers.com/polymer_UBE-UBEPOL-VCR617-Synthetic-Rubber-Vulcanizate-Cured-50-Minutes-at-145C.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	78	78	ASTM D412
Tensile Strength at Break	17.9 MPa	2600 psi	ASTM D412
Elongation at Break	290 %	290 %	ASTM D412
100% Modulus	0.00640 GPa	0.928 ksi	ASTM D412
200% Modulus	0.0133 GPa	1.93 ksi	ASTM D412
Rebound	46 %	46 %	BS.903,PART22
Tear Strength	62.0 kN/m	354 pli	ASTM D624
Abrasion	62	62	Lombourn Abrasion Index (Iwamoto Seisakusyo, Japan); UBE Method
	330	330	Pico Abrasion Index; ASTM D2228
Compression Set	18 %	18 %	Method B, 70°C, 72hrs; ASTM D395

Descriptive Properties	Value	Comments
Cut Generation De Mattia Flexing Machine	Min 300,000 times	ASTM D430
Cut Growth (2mm-->15mm) De Mattia Flexing Machine	Min 10 ⁵ times	ASTM D313
Goodrich Flex, 0.175" Stroke, 55lb, 100°C, P.S.	19%	ASTM D623 (44°C change in temperature)
Wet Skid Resistance on Safety-Walk	23	UBE Method (British Portable Skid Resistance Tester)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China