

Unipetrol PE HD LITEN® BB 75 HDPE

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

Material Notes:

Made for blow molding, extrusion, and pipe applications. Information provided by Unipetrol RPA

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unipetrol-PE-HD-LITEN-BB-75-HDPE.php

Physical Properties	Metric	English	Comments
Density	0.948 g/cc	0.0342 lb/in ³	ISO 1183
ESCR 100% Igepal®	>= 2000 hour @Temperature 50.0 °C	>= 2000 hour @Temperature 122 °F	ASTM D1693
Melt Flow	0.45 g/10 min @Load 5.00 kg, Temperature 190 °C	0.45 g/10 min @Load 11.0 lb, Temperature 374 °F	ISO 1133
	11 g/10 min @Load 21.6 kg, Temperature 190 °C	11 g/10 min @Load 47.6 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	60	60	ISO 868
Tensile Strength, Yield	23.0 MPa	3340 psi	ISO 527
Elongation at Yield	10 %	10 %	ISO 527
Flexural Modulus	1.00 GPa	145 ksi	ISO 178
Charpy Impact, Notched	0.160 J/cm ² @Temperature 23.0 °C	0.761 ft-lb/in ² @Temperature 73.4 °F	ISO 179
	0.600 J/cm ² @Temperature -30.0 °C	2.86 ft-lb/in ² @Temperature -22.0 °F	ISO 179

Thermal Properties	Metric	English	Comments
Vicat Softening Point	124 °C	255 °F	ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China