

Unipetrol PP MONSTEN® FC 908 Polypropylene Random Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Applications include injection molding and packaging films. Slip and antiblocking agent stabilization. Random copolymer. Information provided by Unipetrol RPA

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unipetrol-PP-MONSTEN-FC-908-Polypropylene-Random-Copolymer.php

Physical Properties	Metric	English	Comments
Melt Flow	8.0 g/10 min	8.0 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	24.0 MPa	3480 psi	ISO 527
Elongation at Break	>= 250 %	>= 250 %	ISO 527
Flexural Modulus	0.800 GPa	116 ksi	ISO 178
Charpy Impact, Notched	0.160 J/cm²	0.761 ft-lb/in²	ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	0.550 J/cm²	2.62 ft-lb/in²	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	46.0 °C	115 °F	ISO 75
Vicat Softening Point	132 °C	270 °F	ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China