

Unipetrol PP MONSTEN® MT 935 Polypropylene Random Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Made for injection molding applications. Antistatic and transparent stabilization. Random copolymer. Information provided by Unipetrol RPA

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unipetrol-PP-MONSTEN-MT-935-Polypropylene-Random-Copolymer.php

Physical Properties	Metric	English	Comments
Melt Flow	35 g/10 min	35 g/10 min	ISO 1133
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	26.0 MPa	3770 psi	ISO 527
Elongation at Break	>= 200 %	>= 200 %	ISO 527
Flexural Modulus	1.05 GPa	152 ksi	ISO 178
Charpy Impact, Notched	0.130 J/cm²	0.619 ft-lb/in²	ISO 179
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	0.450 J/cm²	2.14 ft-lb/in²	ISO 179
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	49.0 °C	120 °F	ISO 75
Vicat Softening Point	130 °C	266 °F	ISO 306

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China