

Unitika A1030GFL45 PA6, 45% Glass Fiber Reinforced, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 50% Glass Fiber Filled

Material Notes:

Information provided by Unitika Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unitika-A1030GFL45-PA6-45-Glass-Fiber-Reinforced-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.50 g/cc	0.0542 lb/in ³	ISO 1183
Water Absorption	1.0 % @Time 86400 sec	1.0 % @Time 24.0 hour	ISO 62
Moisture Absorption at Equilibrium	1.5 %	1.5 %	50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0010 cm/cm @Thickness 3.20 mm	0.0010 in/in @Thickness 0.126 in	
Linear Mold Shrinkage, Transverse	0.0030 cm/cm @Thickness 3.20 mm	0.0030 in/in @Thickness 0.126 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	109	109	ISO 2039
Tensile Strength at Break	150 MPa	21800 psi	ISO 527-1/-2
Elongation at Break	4.9 %	4.9 %	ISO 527-1/-2
Tensile Modulus	8.00 GPa	1160 ksi	ISO 527-1/-2
Flexural Strength	220 MPa	31900 psi	ISO 178
Flexural Modulus	7.60 GPa	1100 ksi	ISO 178
Charpy Impact Unnotched	9.20 J/cm ²	43.8 ft-lb/in ²	ISO 179-1
Charpy Impact, Notched	2.30 J/cm ²	10.9 ft-lb/in ²	ISO 179-1

Thermal Properties	Metric	English	Comments
CTE, linear	23.0 µm/m-°C	12.8 µin/in-°F	ISO 11359-2
Flammability, UL94	HB @Thickness 0.860 mm	HB @Thickness 0.0339 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	7.00e+11 ohm-cm	7.00e+11 ohm-cm	IEC 60093
Dielectric Strength	40.2 kV/mm	1020 kV/in	IEC 60243-1
	@Thickness 1.00 mm	@Thickness 0.0394 in	
Dissipation Factor	0.012	0.012	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	550 V	550 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China