

Unitika A1030JR PA6, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

Information provided by Unitika Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unitika-A1030JR-PA6-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ISO 1183
Water Absorption	1.8 %	1.8 %	ISO 62
	@Time 86400 sec	@Time 24.0 hour	
Moisture Absorption at Equilibrium	2.8 %	2.8 %	50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0090 cm/cm	0.0090 in/in	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Linear Mold Shrinkage, Transverse	0.011 cm/cm	0.011 in/in	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	85	85	ISO 2039
Tensile Strength, Yield	55.0 MPa	7980 psi	ISO 527-1/-2
Elongation at Break	150 %	150 %	ISO 527-1/-2
Elongation at Yield	22 %	22 %	ISO 527-1/-2
Tensile Modulus	1.20 GPa	174 ksi	ISO 527-1/-2
Flexural Strength	49.0 MPa	7110 psi	ISO 178
Flexural Modulus	1.20 GPa	174 ksi	ISO 178
Charpy Impact Unnotched	NB	NB	ISO 179-1
Charpy Impact, Notched	3.10 J/cm ²	14.8 ft-lb/in ²	ISO 179-1

Thermal Properties	Metric	English	Comments
CTE, linear	96.0 µm/m-°C	53.3 µin/in-°F	ISO 11359-2
Flammability, UL94	V-2	V-2	
	@Thickness 0.840 mm	@Thickness 0.0331 in	

Thermal Properties	Metric	English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	8.00e+11 ohm-cm	8.00e+11 ohm-cm	IEC 60093
Dielectric Constant	3.7	3.7	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dielectric Strength	33.0 kV/mm	838 kV/in	IEC 60243-1
	@Thickness 1.00 mm	@Thickness 0.0394 in	
Dissipation Factor	0.080	0.080	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	>= 600 V	>= 600 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China