

Unitika A3030N-2 PA6, 30% Mineral Reinforced, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 40% Mineral Filled

Material Notes:

Information provided by Unitika Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unitika-A3030N-2-PA6-30-Mineral-Reinforced-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.43 g/cc	0.0517 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	1.9 %	1.9 %	50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0070 cm/cm	0.0070 in/in	
	@Thickness 3.20 mm	@Thickness 0.126 in	
Linear Mold Shrinkage, Transverse	0.0080 cm/cm	0.0080 in/in	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	49.0 MPa	7110 psi	ISO 527-1/-2
Elongation at Break	13 %	13 %	ISO 527-1/-2
Tensile Modulus	2.00 GPa	290 ksi	ISO 527-1/-2
Flexural Strength	52.0 MPa	7540 psi	ISO 178
Flexural Modulus	2.00 GPa	290 ksi	ISO 178
Charpy Impact Unnotched	5.20 J/cm ²	24.7 ft-lb/in ²	ISO 179-1
Charpy Impact, Notched	0.700 J/cm ²	3.33 ft-lb/in ²	ISO 179-1

Thermal Properties	Metric	English	Comments
CTE, linear	60.0 µm/m-°C	33.3 µin/in-°F	ISO 11359-2
Flammability, UL94	V-2	V-2	
	@Thickness 0.850 mm	@Thickness 0.0335 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China