

Unitika RUN35-TA Light resistant PA6, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Light resistant and internal information provided by Unitika Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Unitika-RUN35-TA-Light-resistant-PA6-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.75 g/cc	0.0632 lb/in ³	ASTM D792
Water Absorption	0.93 %	0.93 %	
Linear Mold Shrinkage, Flow	0.0010 cm/cm	0.0010 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0040 cm/cm	0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	120 MPa	17400 psi	ASTM D638
Elongation at Break	3.3 %	3.3 %	ASTM D638
Flexural Strength	170 MPa	24700 psi	ASTM D790
Flexural Modulus	12.5 GPa	1810 ksi	ASTM D790
Izod Impact, Notched	0.600 J/cm	1.12 ft-lb/in	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China