

Victrex® Vicote® F809 Polyetheretherketone (PEEK) Liquid Dispersion

Category: Polymer, Thermoplastic, Polyketone, Polyetheretherketone (PEEK)

Material Notes:

The VICOTE F808 natural, F809 natural and F810Blk grades have been specifically formulated to provide a resilient coating with high wear and abrasion resistance combined with excellent release properties on ferrous substrates such as carbon and cast steels. These properties are retained at high temperatures where other release coatings would potentially fail. VICOTE dispersions have a low level of extractables. All information provided by Victrex.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Victrex-Vicote-F809-Polyetheretherketone-PEEK-Liquid-Dispersion.php

Physical Properties	Metric	English	Comments
Storage Temperature	5.00 - 25.0 °C	41.0 - 77.0 °F	

Mechanical Properties	Metric	English	Comments
Impact	1.0	1.0	1m, 1kg, Indent 5mm; ISO 6272
Coefficient of Friction	0.090	0.090	μm @ 10 min., Using 250N Load; ASTM G 133

Processing Properties	Metric	English	Comments
Drying Temperature	120 °C	248 °F	overnight before use
	150 °C	302 °F	
	@Time 10800 sec	@Time 3.00 hour	

Descriptive Properties	Value	Comments
Color	Off White	
Konig Hardness (seconds)	125	ISO 1522

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Address: United North Road 215, Fengxian District, Shanghai City, China

Skype: lookpolymers