

Voloknohim PA-TM15 Glass and Mineral Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Information provided by Voloknokhim

Order this product through the following link:

http://www.lookpolymers.com/polymer_Voloknohim-PA-TM15-Glass-and-Mineral-Filled.php

Physical Properties	Metric	English	Comments
Filler Content	12 - 18 %	12 - 18 %	
Particle Size	2000 - 5000 µm	2000 - 5000 µm	at least 97%
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	

Mechanical Properties	Metric	English	Comments
Elongation at Break	>= 6.0 %	>= 6.0 %	
Modulus of Elasticity	4.00 GPa	580 ksi	When curved
Transverse Strength	>= 90.0 MPa	>= 13100 psi	when destroyed
Tear Strength Test	>= 68	>= 68	MPa

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China