

Vyncolit 2920 W Novolac Phenolic

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Phenolic , Phenolic, Novolac, Mineral Filled

Material Notes:

Mineral and organic filled molding compound with good dimensional stability and heat resistance. USES: Carburettor and intake manifold thermal insulator. Information provided by Vyncolit, a Sumitomo Bakelite Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Vyncolit-2920-W-Novolac-Phenolic.php

Physical Properties	Metric	English	Comments
Bulk Density	0.750 - 0.850 g/cc	0.0271 - 0.0307 lb/in ³	Powder Density; ISO 60
Density	1.75 g/cc	0.0632 lb/in ³	Relative Density; ISO 1183
Linear Mold Shrinkage	0.0040 - 0.0050 cm/cm	0.0040 - 0.0050 in/in	Injection Molding; ISO 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	40.0 - 50.0 MPa	5800 - 7250 psi	ISO 527
Elongation at Break	0.65 - 0.75 %	0.65 - 0.75 %	Tensile; ISO 527
	1.2 - 1.3 %	1.2 - 1.3 %	Flexure; ISO 178
Tensile Modulus	10.5 - 12.0 GPa	1520 - 1740 ksi	ISO 527
Flexural Strength	80.0 - 100 MPa	11600 - 14500 psi	At Rupture; ISO 178
Flexural Modulus	6.00 - 8.00 GPa	870 - 1160 ksi	ISO 178
Compressive Strength	200 - 230 MPa	29000 - 33400 psi	ISO 604
Charpy Impact Unnotched	0.650 - 0.800 J/cm ²	3.09 - 3.81 ft-lb/in ²	ISO 179
Charpy Impact, Notched	0.200 - 0.300 J/cm ²	0.952 - 1.43 ft-lb/in ²	ISO 179

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	30.0 - 40.0 $\mu\text{m/m}\cdot^\circ\text{C}$ @Temperature 20.0 $^\circ\text{C}$	16.7 - 22.2 $\mu\text{in/in}\cdot^\circ\text{F}$ @Temperature 68.0 $^\circ\text{F}$	TMA
CTE, linear, Transverse to Flow	40.0 - 50.0 $\mu\text{m/m}\cdot^\circ\text{C}$ @Temperature 20.0 $^\circ\text{C}$	22.2 - 27.8 $\mu\text{in/in}\cdot^\circ\text{F}$ @Temperature 68.0 $^\circ\text{F}$	TMA
Deflection Temperature at 1.8 MPa (264 psi)	150 - 180 $^\circ\text{C}$	302 - 356 $^\circ\text{F}$	ISO 75 Af
Deflection Temperature at 8.0 MPa	130 - 150 $^\circ\text{C}$	266 - 302 $^\circ\text{F}$	ISO 75 C

Thermal Properties	^{V-1} Metric	^{V-1} English	Comments
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	
	@Thickness 4.00 mm	@Thickness 0.157 in	
Shrinkage	0.10 - 0.20 %	0.10 - 0.20 %	Post Shrinkage; ISO 2577

Electrical Properties	Metric	English	Comments
Insulation Resistance	1.00e+10 - 1.00e+11 ohm	1.00e+10 - 1.00e+11 ohm	Dry; IEC 167
Dielectric Strength	25.0 kV/mm	635 kV/in	IEC 243
Comparative Tracking Index	175 V	175 V	IEC 112

Descriptive Properties	Value	Comments
Color	Black	
ISO type	PF 2 C3	
Main Filler	Mineral & Organic	
Molding Method	Compression, transfer, injection	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China