

Washington Penn High Modulus Polypropylene Copolymer 15% Mica Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Mica Filler

Material Notes:

Mica-filled polypropylene compounds provide the best strength and modulus of any of the particulate fillers which results in an outstanding balance of properties. Mold shrinkage is similar to ABS and parts run in ABS tooling may be useable in size and fit. Compounds may also be supplied with very high rigidity and heat deflection temperatures. Information provided by Washington Penn Plastic Co.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Washington-Penn-High-Modulus-Polypropylene-Copolymer-15-Mica-Filled.php

Physical Properties	Metric	English	Comments
Density	1.00 g/cc	0.0361 lb/in ³	ASTM D792
Filler Content	15 %	15 %	
Melt Flow	4.0 g/10 min	4.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	32.4 MPa	4700 psi	ASTM D638
Flexural Modulus	2.00 GPa	290 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	ASTM D256
Gardner Impact	1.81 J @Temperature 23.0 °C	1.33 ft-lb @Temperature 73.4 °F	ASTM D5420

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	113 °C	235 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	62.8 °C	145 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China