

Wellman Wellamid® 22LH-WBK Unfilled Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Unreinforced

Material Notes:

Description: Unfilled Nylon 66 Information provided by Wellman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-22LH-WBK-Unfilled-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in³	ISO 1183-87
Linear Mold Shrinkage, Flow	0.016 - 0.020 cm/cm	0.016 - 0.020 in/in	ISO DIS 294-4
Linear Mold Shrinkage, Transverse	0.018 - 0.022 cm/cm	0.018 - 0.022 in/in	ISO DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	70.0 MPa	10200 psi	ISO 527-93
Elongation at Break	25 %	25 %	ISO 527-93
Flexural Strength	90.0 MPa	13100 psi	ISO 178-93
Flexural Modulus	2.70 GPa	392 ksi	ISO 178-93
Izod Impact, Notched (ISO)	5.00 kJ/m²	2.38 ft-lb/in²	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	ISO 75-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China