

Wellman Wellamid® 22LH13 XE-NBK1 Impact Modified Engineering Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Impact Grade

Material Notes:

Description: Impact Modified Engineering Nylon 66 Information provided by Wellman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-22LH13-XE-NBK1-Impact-Modified-Engineering-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	ISO 1183-87
Linear Mold Shrinkage, Flow	0.017 - 0.021 cm/cm	0.017 - 0.021 in/in	ISO DIS 294-4
Linear Mold Shrinkage, Transverse	0.018 - 0.022 cm/cm	0.018 - 0.022 in/in	ISO DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	70.0 MPa	10200 psi	ISO 527-93
Elongation at Break	45 %	45 %	ISO 527-93
Flexural Strength	85.0 MPa	12300 psi	ISO 178-93
Flexural Modulus	2.40 GPa	348 ksi	ISO 178-93
Izod Impact, Notched (ISO)	12.0 kJ/m ²	5.71 ft-lb/in ²	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	ISO 75-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China