

Wellman Wellamid® FRGFT1741-BK2 Nylon 66, 32% Glass Fiber Reinforced, Flame Retardant

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Glass Fiber Filled, Flame Retardant

Material Notes:

All information provided by Wellman Engineered Resins.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-FRGFT1741-BK2-Nylon-66-32-Glass-Fiber-Reinforced-Flame-Retardant.php

Physical Properties	Metric	English	Comments
Density	1.61 g/cc	0.0582 lb/in ³	ISO 1183-87
Linear Mold Shrinkage, Flow	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	DIS 294-4
Linear Mold Shrinkage, Transverse	0.0070 - 0.011 cm/cm	0.0070 - 0.011 in/in	DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	145 MPa	21000 psi	ISO 527-93
Elongation at Break	2.0 %	2.0 %	ISO 527-93
Flexural Strength	200 MPa	29000 psi	ISO 178-93
Flexural Modulus	10.1 GPa	1460 ksi	ISO 178-93
Izod Impact, Notched (ISO)	8.00 kJ/m ²	3.81 ft-lb/in ²	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	245 °C	473 °F	ISO 75-93
Flammability, UL94	V-0 @Thickness 0.800 mm	V-0 @Thickness 0.0315 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China