

Wellman Wellamid® GFT33NO51-NBK2 33% Glass Fiber Reinforced, Impact Modified Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

Description: Glass Fiber Reinforced, Impact Modified Nylon 66 Information provided by Wellman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-GFT33NO51-NBK2-33-Glass-Fiber-Reinforced-Impact-Modified-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in ³	ISO 1183-87
Filler Content	33 %	33 %	
Linear Mold Shrinkage, Flow	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	ISO DIS 294-4
Linear Mold Shrinkage, Transverse	0.0070 - 0.011 cm/cm	0.0070 - 0.011 in/in	ISO DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	140 MPa	20300 psi	ISO 527-93
Elongation at Break	2.5 %	2.5 %	ISO 527-93
Flexural Strength	190 MPa	27600 psi	ISO 178-93
Flexural Modulus	7.50 GPa	1090 ksi	ISO 178-93
Izod Impact, Notched (ISO)	13.5 kJ/m ²	6.42 ft-lb/in ²	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	230 °C	446 °F	ISO 75-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China