

Wellman Wellamid® GFX1717-N1 43% Glass Fiber Reinforced, Silicone Lubricated Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 40% Glass Fiber Filled

Material Notes:

Description: Glass Fiber Reinforced, Silicone Lubricated Nylon 66 Information provided by Wellman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-GFX1717-N1-43-Glass-Fiber-Reinforced-Silicone-Lubricated-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.50 g/cc	0.0542 lb/in ³	ISO 1183-87
Filler Content	43 %	43 %	
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	ISO DIS 294-4
Linear Mold Shrinkage, Transverse	0.0070 - 0.0090 cm/cm	0.0070 - 0.0090 in/in	ISO DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	210 MPa	30500 psi	ISO 527-93
Elongation at Break	3.5 %	3.5 %	ISO 527-93
Flexural Strength	310 MPa	45000 psi	ISO 178-93
Flexural Modulus	11.8 GPa	1710 ksi	ISO 178-93
Izod Impact, Notched (ISO)	20.0 kJ/m ²	9.52 ft-lb/in ²	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	220 °C	428 °F	ISO 75-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China