

Wellman Wellamid® MRGF25/15 22H-NBK1/WE-1364 40% Mineral/Glass Reinforced Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Glass/Mineral Filled

Material Notes:

Description: Mineral/Glass Reinforced Nylon 66 Information provided by Wellman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wellman-Wellamid-MRGF2515-22H-NBK1WE-1364-40-MineralGlass-Reinforced-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.48 g/cc	0.0535 lb/in ³	ISO 1183-87
Filler Content	40 %	40 %	
Linear Mold Shrinkage, Flow	0.0025 - 0.0065 cm/cm	0.0025 - 0.0065 in/in	ISO DIS 294-4
Linear Mold Shrinkage, Transverse	0.0080 - 0.012 cm/cm	0.0080 - 0.012 in/in	ISO DIS 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	100 MPa	14500 psi	ISO 527-93
Elongation at Break	2.5 %	2.5 %	ISO 527-93
Flexural Strength	165 MPa	23900 psi	ISO 178-93
Flexural Modulus	8.70 GPa	1260 ksi	ISO 178-93
Izod Impact, Notched (ISO)	4.50 kJ/m ²	2.14 ft-lb/in ²	ISO 180-93

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	220 °C	428 °F	ISO 75-93

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China