

Wieland Porta Optimum 880 Solder

Category : Metal , Nonferrous Metal , Precious Metal , Gold Alloy , Solder/Braze Alloy

Material Notes:

Solder supplied as strip (0.18 oz. roll), triangular (7.09 in. rod) Information provided by WielandDental

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wieland-Porta-Optimum-880-Solder.php

Component Elements Properties	Metric	English	Comments
Copper, Cu	9.5 %	9.5 %	
Gold, Au	75.5 %	75.5 %	
Iridium, Ir	0.10 %	0.10 %	
Silver, Ag	12.4 %	12.4 %	
Zinc, Zn	2.5 %	2.5 %	

Processing Properties	Metric	English	Comments
Processing Temperature	882 °C	1620 °F	Flow Temp
Melt Temperature	860 - 882 °C	1580 - 1620 °F	

Descriptive Properties	Value	Comments
Color	yellow	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China