

Wieland Porta Optimum 940 Solder

Category : Metal , Nonferrous Metal , Precious Metal , Gold Alloy , Solder/Braze Alloy

Material Notes:

Solder supplied as strip (0.18 oz. roll)Information provided by WielandDental

Order this product through the following link:

http://www.lookpolymers.com/polymer_Wieland-Porta-Optimum-940-Solder.php

Component Elements Properties	Metric	English	Comments
Gold, Au	89 %	89 %	
Iridium, Ir	0.30 %	0.30 %	
Platinum, Pt	5.0 %	5.0 %	
Zinc, Zn	5.7 %	5.7 %	

Processing Properties	Metric	English	Comments
Processing Temperature	940.0 °C	1724 °F	Flow Temp
Melt Temperature	850.0 - 930.0 °C	1562 - 1706 °F	

Descriptive Properties	Value	Comments
Color	yellow	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China