## Zeon Chemicals Hydrin® T3100 Polyepichlorohydrin Elastomer

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

## Material Notes:

Hydrin T3100 is an epichlorohydrin/ethylene oxide/allyl glycidyl ether terpolymer with high oil, fuel and solvent resistance. Compounds using Hydrin T3100 typically exhibit good heat resistance, excellent ozone resistance along with outstanding gas impermeability. Sufficient antioxidant is added during the manufacturing process for normal aging conditions. High AGE content terpolymer for enhanced "sour gasoline" and ozone resistance.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Zeon-Chemicals-Hydrin-T3100-Polyepichlorohydrin-Elastomer.php

| Physical Properties | Metric              | English             | Comments        |
|---------------------|---------------------|---------------------|-----------------|
| Specific Gravity    | 1.30 g/cc           | 1.30 g/cc           |                 |
| Mooney Viscosity    | 63 - 77             | 63 - 77             | (1+4)           |
|                     | @Temperature 100 °C | @Temperature 212 °F |                 |
| Ash                 | <= 1.0 %            | <= 1.0 %            | Zeon Test #1358 |

| Thermal Properties        | Metric   | English  | Comments |  |
|---------------------------|----------|----------|----------|--|
| Glass Transition Temp, Tg | -36.0 °C | -32.8 °F |          |  |

| Component Elements Properties | Metric        | English       | Comments |
|-------------------------------|---------------|---------------|----------|
| Chlorine, Cl                  | 27.5 - 29.5 % | 27.5 - 29.5 % |          |

| Processing Properties | Metric   | English  | Comments        |
|-----------------------|----------|----------|-----------------|
| Moisture Content      | <= 1.0 % | <= 1.0 % | Zeon Test #1361 |

| Descriptive Properties | Value | Comments |
|------------------------|-------|----------|
| AGE Content, %         | 10-12 |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China