

## Zeon Chemicals Quintone® C200S Aliphatic Hydrocarbon Resin

Category: Polymer, Thermoset, Rubber or Thermoset Elastomer (TSE)

**Material Notes:** 

C5 type (piperylene precursor). Has excellent flowability, heat stability and colors, suitable for traffic paint. Information provided by Zeon Chemicals L.P.

Order this product through the following link:

http://www.lookpolymers.com/polymer\_Zeon-Chemicals-Quintone-C200S-Aliphatic-Hydrocarbon-Resin.php

Physical Properties	Metric	English	Comments
Brookfield Viscosity	140 cP	140 cP	Melt
	@Temperature 200 °C	@Temperature 392 °F	
Molecular Weight	1.25e+6 g/mol	1.25e+6 g/mol	

Thermal Properties	Metric	English	Comments
Softening Point	96.0 °C	205 °F	

Optical Properties	Metric	English	Comments
Gardner Color Number	4.0	4.0	50% in toluene

Chemical Properties	Metric	English	Comments
Acid Value	1.7	1.7	mg KOH/g

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China