

Zircar Refractory Composites ASPA-2 Alumina-Silica Fiber Paper

Category : Ceramic , Oxide , Aluminum Oxide , Silicon Oxide

Material Notes:

ASPA-2 is a premium grade, lightweight refractory material made from high purity alumina-silica fibers formed into highly flexible sheets. This alumina-silica fiber paper exhibits very low thermal conductivity and is designed for use in applications where purity, cracking resistance, high strength and resistance to heat are paramount. Due to its exceptional resistance to heat flow for its thickness, it provides maximum thermal resistance where space is at a premium. This material is virtually shot free and is the cleanest refractory paper available. It is ideal for applications up to 1260°C (2300°F). Type ASPA-2 is produced with no organic volatiles and will not produce smoke or odor when heated. Information provided by ZIRCAR Refractory Composites, Inc. (ZRCI)

Order this product through the following link:

http://www.lookpolymers.com/polymer_Zircar-Refractory-Composites-ASPA-2-Alumina-Silica-Fiber-Paper.php

Physical Properties	Metric	English	Comments
Density	0.128 g/cc	0.00462 lb/in ³	
Loss On Ignition	<= 0.50 %	<= 0.50 %	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.0500 W/m-K	0.347 BTU-in/hr-ft ² -°F	
	@Temperature 500 °C	@Temperature 932 °F	
	0.0800 W/m-K	0.555 BTU-in/hr-ft ² -°F	
	@Temperature 800 °C	@Temperature 1470 °F	
	0.130 W/m-K	0.902 BTU-in/hr-ft ² -°F	
	@Temperature 871 °C	@Temperature 1600 °F	
	0.160 W/m-K	1.11 BTU-in/hr-ft ² -°F	
	@Temperature 1100 °C	@Temperature 2010 °F	
Melting Point	1760 °C	3200 °F	
Maximum Service Temperature, Air	1260 °C	2300 °F	

Component Elements Properties	Metric	English	Comments
Al2O3	51 %	51 %	
SiO2	49 %	49 %	

Descriptive Properties	Value	Comments
Color	White	

Descriptive Properties	Value	Comments
Mullen Burst, psi	20	
Type of Binder	none	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China